

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2001-354949  
(43)Date of publication of application : 25.12.2001

(51)Int. CI. C09K 3/10  
C03C 27/06  
// C08L 51/06

(21)Application number : 2000-175214 (71)Applicant : YOKOHAMA RUBBER CO LTD:THE  
(22)Date of filing : 12.06.2000 (72)Inventor : TAKEYAMA SHUICHI  
IGAWA KATSUHIRO  
WATANABE JIRO

(54) SEALING AGENT COMPOSITION AND DOUBLE GLAZING USING THE SAME

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a sealing material composition which does not need a metal spacer or a secondary sealing material in preparing a double glazing, does not need the use of a primer or an adhesive resin, and is especially useful as a sealing material, and to provide a double glazing the production process of which is greatly simplified because of the use of the composition as a sealing material. SOLUTION: This sealing material composition comprises a continuous phase formed from a non-crystalline polyolefin to which a silane compound having hydrolyzable silyl groups has been grafted and a disperse phase formed from a thermoplastic resin and/or an elastomer and has a moisture permeability of 200 g/m<sup>2</sup>.24h or lower (30 μm thickness).

## LEGAL STATUS

[Date of request for examination]  
[Date of sending the examiner's decision  
of rejection]  
[Kind of final disposal of application  
other than the examiner's decision of  
rejection or application converted  
registration]  
[Date of final disposal for application]  
[Patent number]  
[Date of registration]  
[Number of appeal against examiner's  
decision of rejection]  
[Date of requesting appeal against  
examiner's decision of rejection]  
[Date of extinction of right]

12/7/2005

Copyright (C); 1998, 2003 Japan Patent Office

12/7/2005